

### ISORYL® – modified PPE/PPO

Structure	Amorphous
Density	1.06 g/cm <sup>3</sup> (unfilled)
General properties	Hard, high resilience, high thermal and dimensional stability. Excellent electrical properties.
Barrel temperature	(decrease 15°C for flame retardant grades)
Feed zone:	70 – 100 °C
Zone 1:	240 – 270 °C
Zone 2:	260 – 300 °C
Zone 3:	260 – 300 °C
Zone 4:	260 – 300 °C
Zone 5:	260 – 300 °C
Nozzle:	260 – 300 °C
Melt temperature	280 – 300 °C
Mould temperature	100 – 120 °C
Injection temperature	1100 – 1700 bar
Post-pressure	Between 30 and 60% of injection pressure, medium-high post-pressure time
Counterpressure	50 – 100 bar
Injection speed	High
Screw speed	Equal to peripheric speed of 0.5 m/s
Metering	25 – 80% of barrel volume.
Cushion	5 – 10 mm, depends on metering and screw diameter
Drying	2 hours at 100°C
Recycle	Maximum 20% of regrinded material. This percentage decreases for technical and aesthetic parts.
Shrinkage	0.5 – 0.7% (for unfilled product)
Barrel equipment	Three-section screw, L:D = 25 , non-return valve, free-flow nozzle.
Quenching	Purge with PP or PEHD.